

**Table 3: Seasoned Weights for Wood Stored May 1 thru October 31**

Seasoned Weight Conversion (Lbs per Cord) For Wood Stored May 1 thru October 31 <i>Effective beginning July 1, 2012</i>										
# of Full Weeks Stored	Aspen 100 inch	Aspen Tree Length		Jack Pine	Balsam Fir	Spruce	Balm Gilead	Red Pine	White Pine	Tamarack
	100-inch or Tree Length									
1	4500	4500		4600	4700	4200	4800	4700	4400	5000
2	4500	4500		4600	4700	4200	4800	4700	4400	5000
3	4500	4500		4600	4700	4200	4800	4700	4400	5000
4	4500	4500		4600	4700	4200	4800	4700	4400	5000
5	4375	4457		4390	4406	4067	4600	4300	4300	4700
6	4345	4446		4339	4336	4035	4600	4300	4300	4700
7	4314	4436		4289	4266	4002	4600	4300	4300	4700
8	4284	4425		4239	4198	3970	4600	4300	4300	4700
9	4254	4414		4190	4131	3939	4600	4300	4300	4700
10	4224	4404		4141	4065	3907	4600	4300	4300	4700
11	4195	4393		4093	4000	3876	4600	4300	4300	4700
12	4165	4383		4046	3936	3845	4600	4300	4300	4700
13	4136	4372		3999	3873	3814	4600	4300	4300	4700
14	4107	4362		3953	3811	3784	4600	4300	4300	4700
15	4079	4351		3907	3750	3753	4600	4300	4300	4700
16	4050	4341		3861	3690	3723	4600	4300	4300	4700
17	4022	4330		3817	3631	3693	4600	4300	4300	4700
18	3993	4320		3772	3573	3664	4600	4300	4300	4700
19	3966	4310		3729	3516	3635	4600	4300	4300	4700
20	3938	4299		3685	3459	3606	4600	4300	4300	4700
21	3910	4289		3643	3404	3577	4600	4300	4300	4700
22	3883	4279		3600	3350	3548	4600	4300	4300	4700
23	3856	4268		3559	3296	3520	4600	4300	4300	4700
24	3829	4258		3517	3243	3492	4600	4300	4300	4700
>24	3802	4248		3477	3191	3464	4600	4300	4300	4700

1. Droessler, Terry. (1986) *Rate of Weight Loss in Piled Pulpwood.*
2. Burk, Thomas E. (1990) *Rate of Weight Loss in Piled Black Spruce Pulpwood.*
3. Anttila, Richard. (1992) *Tree Length Aspen Weight Loss Study.*
4. Otis Hall and T.D. Rudolph. (1957) *Weight Loss of Stored Jack Pine Pulpwood.* Minnesota Forestry Notes, No 57.