

**Table 2: Weight to Cord Conversions for use with all Forest Products  
as of **October 29, 2012****

➤ Seasoned Weights in Effect (see Page O-18)

Species Name	Species Code	Weight Per Cord (Lbs)
Ash	01	5000
Elm	02	5500
Silver Maple/Boxelder	03	5000
Red Elm	04	5500
Rock Elm	05	5500
Willow	06	5000
Aspen Species	10	Weighted By Species %
Q. Aspen	12	4500
P. Birch	13	4600
Balm Gilead	14	4800
Cottonwood	15	5000
Largetooth Aspen	16	4500
Mixed Maple	19	5000
Red Maple	21	5000
Sugar Maple (hard)	22	5500
Basswood	23	4600
Yellow Birch	24	5500
Black Walnut	25	5500
Butternut	26	5000
Oak Spp.	30	5500
Red Oak	31	5500
Black Oak	32	5500
White Oak	34	5500
Burr Oak	35	5500
Scarlet Oak	36	5500
White Ash	38	5000
Hackberry	43	5000
Mixed Pine	50	Weighted By Species %
White Pine	51	4400
Norway Pine	52	4700
Jack Pine	53	4600
White Spruce	61	4200
Balsam Fir	62	4700
Black Spruce	71	4200
Tamarack	72	5000
N. White Cedar	73	2900
Mixed Spruce	80	4200
Biomass*	98	Weighted By Species %